

Item No.: AA403 High Stretch Fabric

Application

Geometric, Tradeshow, Grandformat, Table stretch

Technical Specifications

Base Material	100% polyester	DIN 60001, ASTM D7641
Yarn	75D*75D	DIN EN 2060, ASTM D1907
Weave Method	Warp-knitted 2 bar	---
Weight	255 ± 10gsm	ISO536
Thickness	600 ± 50 μ m	ISO534
Opacity	≥ 85%	ISO2471
Whiteness	165 ± 10	ISO11475
Color	L: 88.0 ± 2.0; a: 8.5 ± 2.0; b: -20.0 ± 2.0	---
Gloss[60°]	4 ± 2	---
Elasticity	Warp:(10 ± 3)% Weft:(30 ± 5)%	Length*Width=200*50mm, Speed=100mm/min, Tension=20N
Shrinkage	≤ 2%	200° C, 45s
Yellowing ΔE	≤ 2	200° C, 45s
Flame Resistance	DIN 4102-1 B1, NFPA 701	DIN 4102-1 B1, NFPA 701
Recommend Fixation Temperature	190-200°C, 45s	---
Yellowing Temperature	≥ 210°C	SUPRKC REX-C400, 30s

Size

Width	1.60 m/2.60 m/3.20 m	Standard	DIN EN ISO 3759, ASTM D751-2006
Length	50 m	Standard	DIN EN ISO 3759, ASTM D751-2006

Storage Instructions

The product should be stored in the original packaging for protection.

It is recommended to keep it sealed and placed horizontally to avoid direct sunlight and direct contact with heat sources. Recommended storage temperature and humidity: 15° C [59° F] ~ 35° C [95° F], 20 ~ 65% RH; Under this condition, the product shelf life is 1 year.

Features



Compatible Inks

