

Item No.: 4001 Satin Cold Laminated Film

Application

Cold Laminated Film

Technical Specifications

PVC Film	7S Transparent Matte Film	DIN EN ISO 2060,ASTM D1907
PVC Film Weight	80 ± 8gsm	GB/T 451.3-2002
Film Thickness	70 ± 5 μ m	ISO534
Glue	Perpetual Transparent Adhesive	DIN EN ISO 2060,ASTM D1908
Glue weight	24 ± 4gsm	GB/T 451.3-2002
Liner	140g/SSPE	DIN EN ISO 2060,ASTM D1909
Weight	250 ± 20gsm	ISO536
Thickness	230 ± 30 μ m	ISO534
Peel Strength [[bf/in] 15min [[bf/in]	3.0-4.0	FTM1-FINAT
Peel Strength [[bf/in] 24hrs [[bf/in]	4.0-5.0	FTM1-FINAT
Gloss[60°]	>30	GB/T 9754-2007

Size

Width	1.27 m/1.37 m/1.52 m	Standard	DIN EN ISO 3759, ASTM D751-2006
Length	50 m	Standard	DIN EN ISO 3759, ASTM D751-2006

Storage Instructions

The product should be stored in the original packaging for protection.
It is recommended to keep it sealed and placed horizontally to avoid direct sunlight and direct contact with heat sources.Recommended storage temperature and humidity: 15° C [59° F] ~ 35° C [95° F], 20 ~ 65% RH;
Under this condition, the product shelf life is 1 year.

Features



Compatible Inks

Print is
not
suitable